



DESIGN FACTORS TO USE WITH AS 2566

Bedding constant, $R = 0.100$

Deflection lag factor, $L = 1.40$

50 year tensile creep modulus, $E_c = 690 \text{ N/mm}^2$

Modulus of soil reaction, $E' = Y/(Dm/t) \text{ N/mm}^2$

Yfactor = 83 N/mm^2



DETAIL:

TYPICAL PVC PIPE BEDDING DETAIL

Engineering
Quality
Standards

DETAIL No:
D1

MANUKAU CITY COUNCIL

UPDATED:
MAY 1995